

GUARDIAN Butylwrap 1032-40 is a cold applied tape coating system designed for anti corrosion of field joint, fittings, and specialty piping. The adhesive is a key in-ground performance characteristic coupled with high density polyethylene backing. The versatile tape system can be applied by hand or with a wrapping machine.

APPEARANCES

Guardian Butylwrap 1032-40 is a heavy duty adhesive, high tack adhesive, good conformability and consistent uniform thickness, conformable to irregular shapes and worldwide reference lists. Also, it can be applied over a wide temperature range, resistant to UV, easily applied with no special equipment and comply with AWWA standard C209, C214 and ASTM D 1000 Standard cold applied.

ADVANTAGES

It ensures a strong bond and impervious seal. It is very fast and easy for installation and establish in ground history. Additional, it offers a solution for nearly every application. It is versatile and reliable in which is a high performance corrosion protection.

PROPERTIES

Physical Properties	Test Method	Typical Value	
		English	Metric
Total thickness	ASTM D 1000	40.00 mil	1.00 mm
Backing thickness	ASTM D 1000	15.00 mil	0.38 mm
Adhesive thickness	ASTM D 1000	25.00 mil	0.62 mm
Width	-	2" - 6"	50 - 150 mm
Length	-	100'	30 m
Backing colour	-	Black, Yellow, Gray or others	
Tensile strenght	ASTM D 1000	55 N/cm	
Elongation	ASTM D 1000	450%	
Peel Adhesion to primed steel pipe	ASTM D 1000	30 N/cm	
Cathodic Disbandment	ASTM G8	0.25 in radius 6.4 mm	
Dielectric Strength	ASTM D 149	42 kV	
Volume Resistivity	ASTM D 257	1.25x10 ¹² ohm.cm	
Water Absorptivity	ASTM D 570	0.10%	
Water Vapor Transmission	ASTM D 1249	0.01g/100sq in/24h	0.1g/100sq mm/24hRate (24h)
Application Temperature		14°F-140°F	-10°C - 60°C
Max Service Temperature		-40°F-176°F	-40°C - 80°C

PRODUCTS

(BUTYLWRAP 1032-40) Color: Black

Part No.	Weight	Length
FGCS0079	50 mm	15 m
FGCS0080	100 mm	15 m
FGCS0081	150 mm	15 m

All statements and data presented herein are given in good faith and believed to be appropriate and reliable. It is given without express or implied warrant or guarantee. Potential users of Guardian's materials are urged to conduct confirmatory trials to satisfy themselves as to the suitability of the selected product for their particular end use prior to purchase.